

ACF BX11

TECHNICAL DATA SHEET

GEOGRID

ACF BX11 geogrid is composed of polypropylene resin which is extruded into a stable geogrid structure. ACF BX11 geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

ACF BX11 geogrid increases roadbed and foundation bearing capacity, while prolonging the service life of each by the confinement of the base course. ACF BX11 prevents lateral spreading of the base or sub-base aggregate and allows for shear interaction to develop between the aggregate and the geogrid.

ACF BX11 geogrid reduces the applied vertical pressure of heavy loads at depth of aggregate by spreading the load over a wider area.

SPECIFICATIONS:

The ACF BX11 Geogrid will utilize the following characteristics:

PROPERTY	TEST METHOD	TYPICAL ROLL VALUE	
		MD	CMD
Ultimate Tensile Strength ¹	ASTM D6637	850 lbs/ft	1300 lbs/ft
Tensile Strength at 2% ¹	ASTM D6637	280 lbs/ft	450 lbs/ft
Tensile Strength at 5% ¹	ASTM D6637	580 lbs/ft	920 lbs/ft
UV Resistance	ASTM D4355	100%	
Junction Efficiency ²		93%	
Flexural Stiffness ³		250,000 mg-cm	
Resistance to UV Degradation ⁵	ASTM D4355	100%	
Rib Thickness		0.03 in	
Aperture Size		1.0 in	1.3 in
Roll Size (width x length)		13.1 X 246 ft	
Roll Weight		250 lbs	
Roll Area		358 yd ²	

¹True resistance to elongation when initially subjected to a load determined in accordance with ASTM D 6637 without deforming test materials under load before measuring such resistance or employing "secant" or "offset" tangent methods of measurement so as to overstate tensile properties.

²Load transfer capability calculated as a % of ultimate tensile strength.

³Resistance to bending force determined in accordance with ASTM D 5732. The overall Flexural Stiffness is calculated as the square root of the product of MD and CMD Flexural Stiffness values.

⁴Resistance to in-plane rotational movement measured by applying a 20kg-cm (2 m-N) moment to the central junction of a 9 inch x 9 inch specimen in accordance with U.S. Army Corps of Engineers Methodology for measurement of Torsional Rigidity.

⁵Tested according to ASTM D 4355.

Disclaimer: ACF Environmental assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product.