



# PYRAMAT®

## Product Data

### PYRAMAT® 25 TRM

PYRAMAT® 25 turf reinforcement mat (TRM) is a three-dimensional, lofty, woven polypropylene geotextile that is available in green which is specially designed for erosion control applications on steep slopes and vegetated waterways. The matrix is composed of polypropylene monofilament yarns featuring X3® technology woven into a uniform configuration of resilient pyramid-like projections. The material exhibits very high interlock and reinforcement capacity with both soil and root systems, demonstrates superior UV resistance, and enhances seedling emergence. The expected design life of PYRAMAT® 25 is up to 25 years because of its superior UV resistance, resistance to corrosion, strength, and durability in the most demanding environments.

PYRAMAT® 25 conforms to the property values listed below<sup>1</sup> and is manufactured at a Propex facility having achieved ISO 9001:2008 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>ORIGIN OF MATERIALS</b>			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
<b>PHYSICAL</b>			
Mass/Unit Area <sup>4</sup>	ASTM D-6566	8.0 oz/yd <sup>2</sup>	271 g/m <sup>2</sup>
Thickness <sup>2</sup>	ASTM D-6525	0.25 in	6.4 mm
Light Penetration (% Passing) <sup>3</sup>	ASTM D-6567	35%	35%
Color	Visual	Green or Tan	
<b>MECHANICAL</b>			
Tensile Strength <sup>2</sup>	ASTM D-6818	2000 x 1800 lbs/ft	29.2 x 26.3 kN/m
Elongation <sup>2</sup>	ASTM D-6818	20 x 20 %	20 x 20 %
Resiliency <sup>2</sup>	ASTM D-6524	70%	70%
Flexibility <sup>4</sup>	ASTM D-6575	0.195 in-lb	225,000 mg-cm
<b>ENDURANCE</b>			
UV Resistance % Retained at 1,000 hrs <sup>4</sup>	ASTM D-4355	90%	90%
UV Resistance % Retained at 3,000 hrs <sup>4</sup>	ASTM D-4355	90%	90%
<b>PERFORMANCE</b>			
Velocity (Vegetated) <sup>4, 5</sup>	Large Scale	20 ft/sec	6.1 m/sec
Shear Stress (Vegetated) <sup>4, 5</sup>	Large Scale	12 lb/ft <sup>2</sup>	575 Pa
Manning's n (Unvegetated) <sup>4, 6</sup>	Calculated	0.028	0.028
Seedling Emergence <sup>4</sup>	ASTM D-7322	255%	255%
<b>ROLL SIZES</b>		8.5 ft x 120 ft	2.6 m x 36.6 m

**NOTES:**

- The property values listed above are effective 03/09/2018 and are subject to change without notice. Values represent testing at time of manufacture.
- Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
- Maximum Average Roll Value (MaxARV), calculated as the typical plus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will meet to the value reported.
- Typical Value.
- Maximum permissible velocity and shear stress has been obtained through vegetated testing programs featuring specific soil types, vegetation classes, flow conditions, and failure criteria. These conditions may not be relevant to every project nor are they replicated by other manufacturers. Please contact Propex for further information.
- Calculated as typical values from large-scale flexible channel lining test programs with a flow depth of 6 to 12 inches.



ENGINEERED EARTH ARMORING SOLUTIONS™

[www.propexglobal.com](http://www.propexglobal.com)

Propex Operating Company, LLC · 4019 Industry Drive · Chattanooga, TN 37416 · ph 800 621 1273 · ph 423 855 1466

ARMORMAX®, PYRAMAT®, LANDLOK®, X3®, PYRAWALL™, SCOURLOK™, GEOTEX®, PETROMAT®, PETROTAC®, REFLECTEX®, and GRIDPRO™ are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.